



## Product Data

### Castrol Braycote 194

Corrosion Preventive Compound Solvent Cutback  
Cold Application, Transparent, Non-Tacky Film

#### Description

Castrol Braycote™ 194 is a dark brown, liquid corrosion preventive compound intended for indoor exposure. It is a solvent cutback material designed for cold application, and dries in approximately two hours, leaving a firm, amber, transparent film that will not flow below 175°F (80°C).

#### Application

Braycote 194 is designed to protect unpainted metal surfaces from the effects of indoor or shed exposure for periods up to one year. It is non-corrosive and readily wets the surfaces of commonly used metals, leaving a continuous film after evaporation of the solvent. This product may be applied by spray, dip or brush. A gallon will cover approximately 300 to 1,600 square feet, leaving a film 1 to 4 mils thick, depending upon method of application and surface geometry. Optimal performance can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. It is recommended that the metal substrate and ambient temperature be 50-95°F (10-35°C) at the time of product application.

#### Removal

Braycote 194 can be removed from exposed surfaces by vapor degreasing, hot caustic, steam, or petroleum solvents.

#### Specification

Braycote 194 meets the requirements of and is qualified to MIL-PRF-16173E, Class I, Grade 4.



## Typical Characteristics

Test	Method	Units	MIL-PRF-16173E CLASS I, GRADE 4 REQUIREMENTS	Result
Film Characteristics Transparency	Spec 4.6.11.7	Pass/Fail	Continuous and no cracks Pass	Pass
Nonvolatile Content	Spec 4.6.5.1	%	54.0 - 60.0	55.3
Solvent Distillation Endpoint	Spec 4.6.1 ASTM D86	°C/°F	212/410 Maximum	Pass
Sprayability @4 °C/40 °F, 35 psig Flow rate Quality of Coverage	Spec 4.6.7	gm/sec Report	1.0 Minimum Continuous	10.8 Pass
Corrosion, 7 days @55 °C/130 °F, Wt Change Brass Cadmium Zinc Magnesium Aluminum Steel	Spec 4.6.8	mg/cm2	±1.0 Maximum ±5.0 Maximum ±7.5 Maximum ±0.5 Maximum ±0.2 Maximum ±0.2 Maximum	-0.108 -1.473 -1.424 -0.023 -0.003 -0.007
Sulfated Residue	ASTM D874	%	3.96 - 4.82	4.48
Flash Point, PMCC	ASTM D93	°C/°F	38/100 Minimum	41/106
Removability	Spec 4.6.10.1	Pass/Fail	Pass	Pass
Film Thickness	Spec 4.6.11.2	Mils	2.0 Maximum	1.0
Humidity Cabinet	Spec 4.6.11.3	days	30 Days Minimum	Pass (30+)
Salt Spray, Days	Spec 4.6.11.4	days	14 Days Minimum	Pass (17+)
Flow Point, 4 Hrs @80 °C/175 °F	Spec 4.6.15	Pass/Fail	Pass	Pass
Low Temperature Adhesion	Spec 4.6.12	Pass/Fail	No Flaking	Pass
Pour Point	ASTM D97	°C/°F	Report	-18/0
Film Drying and Tackiness	Spec 4.6.13	Pass/Fail	Pass	Pass
Volatile Organic Content	Spec 4.6.5.2	Report	> 2.8 lbs/gal	3.24
Stability	Spec 4.6.6	Pass/Fail	Pass	Pass

Subject to usual manufacturing tolerances.

Health, safety and environmental information are provided for this product in the Materials Safety Data Sheet. This gives details of potential hazards, precautions and First Aid measures, together with environmental effects and disposal of used Products. User accepts all risks and liabilities if the product is used other than in the manner, with the precautions, or for the purpose(s) specified. Before using the product other than directed, please contact Castrol ILS for consultation.

Braycote 194  
07.30.2007  
Castrol, Braycote and the Castrol logo are trademarks of Castrol Limited.

All reasonable care has been taken to ensure that the information contained in this publication is accurate as of the date of printing. However, such information may, nevertheless, be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol Ltd products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product.

Castrol Industrial North America Inc. 150 West Warrenville Road, 605 3E Naperville, IL 60563  
Tel: (877) 641 1600 Fax: (877) 648 9801

[www.castrol.com/industrial](http://www.castrol.com/industrial)