



Rock Drill Oil

Conoco® Rock Drill Oil is an adhesive, extreme-pressure lubricant specially developed for the lubrication of air-powered tools such as rock drills, jackhammers, pavement breakers and drifters. It also may be used for the lubrication of machine tool slideways.

Rock Drill Oil is specially formulated to provide excellent protection for pneumatic percussion tools. It has high load-carrying capacity to protect against wear and seizure of sliding metal surfaces under heavy or shock-load conditions. It has good adhesiveness to metal surfaces in the presence of moisture, and contains inhibitors to protect against rust and corrosion. It has good oxidation resistance and thermal stability at high temperatures for long service life.

Applications

- Pneumatic equipment such as drifters, jackhammers, pavement breakers, rock drills and stoppers
- Slideways on machine tools such as boring machines, grinders, milling machines and planers

Features/Benefits

- Excellent extreme-pressure properties
- Protects against wear and seizure
- Good adhesiveness to metal surfaces in the presence of moisture
- Good oxidation resistance and thermal stability
- Protects against rust and corrosion
- Low odor
- Good foam resistance
- Seven viscosity grades for use over a wide range of temperatures

**Extreme-Pressure
Air Tool Lubricant**

Contact Information

**U.S. Customer
Service:**
1-800-640-1956

Technical Hot Line:
1-800-255-9556

**International
Customer Service:**
+1-832-486-3363
+1-832-486-3870

E-mail address:
*conocolubricants@
conocophilips.com*

www.lubes.conoco.com

600 N. Dairy Ashford • 2W9000 • Houston, TX 77079



Rock Drill Oil
Typical Properties

ISO Grade	32	46	68	100	150	220	320
Specific Gravity @ 60°F	0.861	0.866	0.872	0.880	0.891	0.897	0.903
Density, lbs/gal @ 60°F	7.18	7.22	7.27	7.34	7.43	7.48	7.53
Color, ASTM D1500	1.0	1.0	3.0	3.5	4.5	5.0	5.5
Flash Point (COC),							
°C	199	215	220	220	227	235	250
°F	390	419	428	428	441	455	482
Pour Point,							
°C	-37	-37	-27	-26	-21	-15	-12
°F	-35	-35	-17	-15	-6	5	10
Viscosity,							
cSt @ 40°C	32.0	46.0	70.0	102	160	230	323
cSt @ 100°C	5.6	7.1	9.3	12.3	16.0	20.2	25.2
SUS @ 100°F	165	237	362	529	839	1,214	1,716
SUS @ 210°F	45.0	50.0	57.7	68.8	83.9	102	125
Viscosity Index	116	110	109	113	103	101	101
Falex EP Load, ASTM D3233, lbf	2,250	2,250	2,250	2,250	2,250	2,250	2,250
Foam Test, ASTM D892	Pass	Pass	Pass	Pass	Pass	Pass	Pass
Rust Test, ASTM D665 A	Pass	Pass	Pass	Pass	Pass	Pass	Pass
Timken OK Load, ASTM D2782, lb	60	60	60	60	60	60	60

Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3.conocophillips.com/NetMSDS>.

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

Copyright © 2009 ConocoPhillips Company. The ConocoPhillips logo, Conoco, and the Conoco logo are trademarks of ConocoPhillips Company in the U.S.A. and other countries.