



## Open Gear Lubes 585 NC and 585 NCW

Conoco Open Gear Lubes 585 NC and 585 NCW are viscous, adhesive, asphaltic-based lubricants cut back with a volatile, non-chlorinated solvent for ease of application. They are recommended for the lubrication and cushioning of open and semi-enclosed gears, such as those found in heavy equipment used in underground and surface mines, in rock quarries and for excavation.

Open Gear Lubes 585 NC and 585 NCW are formulated with high-quality paraffinic base oils, resins and asphalt. They are compounded with ashless extreme-pressure additives to provide high load-carrying capacity to protect heavily loaded gears from scoring and galling. They form a heavy, tenacious film (after solvent evaporation) that adheres well to metal surfaces and will not harden or flake off, even at low temperatures. This film provides good resistance to water washout and protects against corrosion.

Open Gear Lube 585 NC is recommended for use at temperatures above 0°F (-18°C), where pumpability is not an issue. Open Gear Lube 585 NCW has a higher solvent content for easier pumpability in colder weather, and may be used at temperatures above -40°F (-40°C).

### **Applications**

- Open and semi-enclosed gears, such as those found on mining equipment, draglines, power shovels, ball and rod mills, cement mills, drying kilns, and papermaking machinery and presses
- Guides and sliding surfaces with large clearances, where asphaltic-type lubricants are specified
- Cables on draglines, clamshells, shovels, hoists and other cable-operated equipment where cable clamp safety devices are not used

Open Gear Lubes 585 NC and 585 NCW meet the performance requirements of:

- AGMA Standard 9005-E02

### **Features/Benefits**

- Excellent adhesion to metal surfaces

**Chlorine-Free,  
Solvent-Cutback  
Open Gear  
Lubricants**

**U.S. Technical  
Services Hot Line:  
1-800-255-9556**

**U.S. Customer  
Service:  
1-800-640-1956**

**International:  
+1-832-486-3363**

**E-mail address:  
*conocolubricants@  
conocophillips.com***

***www.lubes.conoco.com***

600 N. Dairy Ashford • 2W9000 • Houston, TX 77079



- Forms a heavy, tenacious film to lubricate and cushion gear teeth
- Good extreme-pressure properties for protection under heavy or shock loads
- Good resistance to water washout
- Protects against corrosion
- Will not flake off at low temperatures
- Does not contain any chlorine, lead or carcinogens
- Easy application, by pressure gun, brush, swab or drip cup<sup>(1)</sup>

<sup>(1)</sup> **Caution:** These products contain solvent. Proper ventilation and fire safety precautions must be taken during application.

### Open Gear Lubes 585 NC and 585 NCW

#### Typical Properties

Grade	585 NC	585 NCW
Density, g/cm <sup>3</sup> @ 15.6°C (60°F)	0.978	0.979
Density, lbs/gal @ 15.6°C (60°F)	8.14	8.15
Color, Visual	Black	Black
Flash Point (COC), with solvent, °C (°F)	>148 (>298)	110 (230)
Solvent Content, wt %	12	26
Viscosity, without solvent:		
cSt @ 40°C (calculated)	18,143	18,143
cSt @ 100°C	801	801
SUS @ 100°F (calculated)	84,038	84,038
SUS @ 210°F	3,736	3,736
Copper Corrosion, ASTM D130	1b	1b
Four-Ball EP, ASTM D2596, Weld Load, kgf	400	400
Four-Ball Wear, ASTM D2266, Scar Diameter, mm	0.50	0.50
Rust Test, ASTM D665 A&B	Pass	Pass
Timken OK Load, ASTM D2782, lb	45	45
Minimum Application Temperature,		
°C	above -18	above -40
°F	above 0	above -40

#### Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3.conocophillips.com/NetMSDS>.

Due to continual product research and development, the information contained herein is subject to change without notification.

Copyright © 2008 ConocoPhillips Company. The ConocoPhillips logo, Conoco, and the Conoco logo are trademarks of ConocoPhillips Company in the U.S.A. and other countries.